

SOR TESTING LABORATORIES, INC.

Geotechnical Engineering - Materials Testing - Forensic Studies
98 Sand Park Rd., Cedar Grove, NJ 07009
(973) 239-6001 Fax (973) 239-8380

Branch Office:
New Brunswick, NJ
(732) 494-4481

Kamil Sor, Ph.D.
Orhun Sor, P.E.
Peter G. Micklus, P.E.
Yilmaz Arhan, Ph.D.
Kenneth Rowbotham, P.E.

This report is the confidential property of the Client, and information contained may not be published or reproduced without our written permission.

Client: The Schundler Company

Project: Information of Client

Subject: Laboratory Tests of Sprayed-on Fireproofing Material,
Schundler Classic 5 LD (unidentified contractor)

Job No.: 04-504 Report No.: 04-5418 Date: 11/19/2004


The following are test results of the fireproofing material samples applied by an un-identified contractor for the Schundler Company in October, 2004. As requested, the samples were tested only for few properties. The test methods and results were as follows:

TEST RESULTS

Property	ASTM Method	Results
Thickness, inches	E-605	1.19
Density, lbs/cu. ft.	E-605	18.0
Bond Strength, lbs/sq. ft.	E-736	350+

Very truly yours,

SOR TESTING LABORATORIES, INC.


Kamil Sor, Ph. D.
President

KS/ls

cc: (1) Client, Attn: Bruce Schundler
Fax 732-287-4185